

Specialty Materials™



THE BEST GARMENT DECORATION PRODUCTS

New! Blackboard

Blackboard
BB-4950

- Turbo adhesive allows a low temperature and quick press time, which eliminates press marks
- Durable, weeds easily, and has a soft hand and strong grip
- Chalk can be wiped away easily with a wet cloth
- Pressure-sensitive carrier enables easy weeding and repositioning

Acceptable Fabrics

Cotton, Uncoated Polyester, Fabric Blends, Spandex, Lycra, Wool, Linen, and Nylon (See separate pressing Instructions for Nylon)

Sizing Available

Available Widths (in.): 15" and 20"
Available Lengths (ft.): 15', 30', 45', 60', 90', and 150' rolls

Thickness

3.7 mils/95 microns

Application Instructions for Cotton, Polyester, & Cotton/Polyester Blends



45° Blade



Cut this material in mirror image



270°F



Medium, even pressure



Press for 5 Seconds



Peel warm



Turn inside-out and wash normal. Dry at a normal dryer setting on household machines. Do not iron directly onto this material. Dry temperature should not exceed 212°F. Suitable for dry-cleaning.



Application Instructions for Nylon



45° Blade



Cut this material in mirror image



300°F



Low, even pressure



Pre-press garment for 5 seconds, press material for 5 seconds



Peel warm, cover with silicone sheet and re-press for 10 seconds



Turn inside-out and wash normal. Dry at a normal dryer setting on household machines. Do not iron directly onto this material. Dry temperature should not exceed 212°F. Suitable for dry-cleaning.

Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics.